



THE FINEST AUTOMOTIVE REFINISHING TECHNOLOGY

WET ON WET SEALER & PRIMER

ENHANCED LEVELLING AND SEALING PROPERTIES
CAN BE TINTED WITH 8% GERMA-TECH 2K COLOUR



GP3201 - GREY
GP3201B - BLACK
GP3201W - WHITE



2K WET ON WET PRIMER

2K SPEED PRIMER GP3201 | 2K SPEED HARDENER GP3202

USE ON: SANDED EXISTING FINISHES / OEM PANELS /
FIBREGLASS / EPOXY PRIMED SURFACES / PLASTIC PRIMED
SURFACES / BODY FILLER / SANDED METALS INCLUDING
GALVANISED STEEL, IRON, STEEL, & ALUMINIUM.

TINTING: CAN BE TINTED WITH 8% GERMA-TECH
2K COLOUR

WWW.GERMATECH.COM.AU

sales@germatech.com.au

MIXING:

MIX BY VOLUME
3:1:3 (100% REDUCER)

DRY TIME:

FLASH OFF 1 MIN BETWEEN COATS
ALLOW 10-15 MIN FOR PRODUCT
TO APPEAR FULLY MATTE THEN TOPCOAT

MICRONS:

2-3 COATS:
25-35 UM (MICRON) MAX
Do not exceed micron max as
product shrinkage may accrue