



STRICTLY
FOLLOW TECHNICAL
DATA SHEETS

TEXTURE COAT TINTABLE 2K TEXTURE

- POLYURETHAN ACRYLIC
- HIGH BUILD TEXTURE COAT
- TINTABLE WITH GERMATECH 2K COLOUR

TEXTURE COAT 2K TINTABLE

TINTABLE GPFUNC10 | BLACK SATIN GPFUN3063

WWW.GERMATECH.COM.AU

sales@germatech.com.au

USE ON : SUITABLE ON PRIMED AND PREPARED SURFACES INCLUDING METAL TIMBER PLASTIC (REFER TDS)

TINTING: COMPATIBLE WITH GERMATECH 2K COLOUR SYSTEM – TINT 50/50 ON STANDARD COLOURS.

HARDEN : HARDEN IN RATION OF 4 :1 MIXED PRODUCT WITH GERMATECH MS HARDENER

MIXING:

MIX BY VOLUME

2 PARTS TEXTURE

2 PARTS 2K PAINT

1 PART HARDENER

1 PART REDUCER

SPRAY USING SHULTZ GUN OR HIGH-VOLUME TIP

DRY TIME:

FLASH OFF 60 MIN BETWEEN COATS

ADJUST FLASH OFF FOR COATING
THICKNESS AND TEMPERATURE

ALLOW 15 - 20 MIN IF BAKING

AIRDRY 48-72 HOURS AT 20°C

MICRONS:

1-3 COATS

150-450 UM (MICRON)

FULLY CURE UP TO 7 DAYS

THICKNESS OF COATING WILL EFFECT
CURE TIME