

BODYFILLER



GP201 LIGHT WEIGHT BODYFILLER

DESCRIPTION:

1. 2 component polyester putty with BPO hardener, light weight
2. Perfect adhesion. Fast drying, easy sanding, light weight, stable storage



Substrates		Sanded galvanized steel, aluminum, steel or epoxy primer
Surface Cleaning		Remove wax, silicon, and other contaminations with degreaser
Mixing Ratio		BodyFiller: Hardener = 50: 1(by weight)
Application Life		3-5minutes (25°C)
Drying Time	Wet-Sanding	9 minutes (25°C)
	Dry-Sanding	20minutes (25°C)
Sanding Grit		P80-180
Density(g/cm3)		1.0 – 1.2
Not suitable substrates		Thermoplastic paint, plastic primer, etch primer
Shelf Life		12 months in original sealed can at cool and dry place at 20°C
Package		1.5kgs*4 cans per box