




THE FINEST AUTOMOTIVE REFINISHING TECHNOLOGY

FAST DRY EPOXY PRIMER

RUST PROOFING FOR BARE METAL, ENHANCED ADHESION POWER



STRICTLY FOLLOW
TECHNICAL DATA SHEETS

FAST DRY EPOXY PRIMER

WWW.GERMATECH.COM.AU

sales@germatech.com.au

USE ONSUITABLE PREPARED: SANDED EXISTING FINISHES
SANDED STEEL, IRON, ALUMINIUM, GALVANISED STEEL,
FIBREGLASS

EPOXY PRIMER GP3401F | EPOXY HARDENER GP3402F | EPOXY REDUCER GP3403F

MIXING:

MIX BY VOLUME

3.5:1:1 (30-35% REDUCER)

ONLY USE EPOXY REDUCER

DRY TIME:

FLASH OFF 5-10 MIN BETWEEN COATS

ALLOW 15-20 MIN BEFORE BAKE

BAKE 45 MIN AT 60°

(AIR DRY 4-6 HOURS AT 20°)

BAKE IN TEMPERATURES BELOW 10°

MICRONS:

2-3 COATS:

40-60 UM (MICRON) MAX

COATABLE WET ON WET AFTER ~1 HOUR

OR SUFFICIENTLY DRY

NON SANDING 8 HOURS - SCUFF SAND

THEREAFTER