



THE FINEST AUTOMOTIVE REFINISHING TECHNOLOGY

2K PRIMER SURFACER HI FILL

- EXTRA HIGH BUILD PRIMER *REQUIRES 25-30% REDUCER*
- ENHANCED FILLING POWER & FINE ADHESION
- FLEXIBILITY AND IMPACT RESISTANCE
- INCREASES GLSS BUILD IN TOPCOAT



STRICTLY FOLLOW
TECHNICAL DATA SHEETS

2 PACK PRIMER SURFACER

2K PRIMER-GP3101 | 2K PRIMER HARDENER-GP3102
ALSO AVAILABLE SLOW HARDENER GP3102S AND FAST HARDENER GP3102F

WWW.GERMATECH.COM.AU

sales@germatech.com.au

USE ON: SUITABLE ON EPOXY PRIMED SURFACES
OR SOME CORRECTLY PREPARED METAL SURFACES
(REFER TDS)

TINTING: CAN BE TINTED WITH 8% GERMA-TECH
2K COLOUR

MIXING:

MIX BY VOLUME

4:1 (25-30% REDUCER)

MUST SPRAY USING

1.4-1.8MM TIP

2-2.5 BAR HVLP

DRY TIME:

FLASH OFF 5 MIN BETWEEN COATS

ALLOW 15-20 MIN BEFORE BAKE

BAKE 45 MIN AT 60°

(AIR DRY 4-6 HOURS AT 20°)

MICRONS:

2-3 COATS

50-80 UM (MICRON) MAX

Do not exceed micron max