



STRICTLY
FOLLOW TECHNICAL
DATA SHEETS

ACRYLIC BINDER BASECOAT TO ACRYLIC

- MIXED 50-60% GERMATECH BASECOAT WITH
- 50-40% ACRYLIC BINDER
- SINGLE COMPONENT HIGH GLOSS HOLD OUT ACRYLIC
- AVAILABLE IN GLOSS SATIN AND MATT FINISH

ACRYLIC BINDER SINGLE PACK

GLOSS GPFEXC100 | SATIN GPFEXC30 | MATT GPFEXC10

USE ON : SUITABLE ON PRIMED AND PREPARED SURFACED (REFER TDS)

WWW.GERMATECH.COM.AU

sales@germatech.com.au

TINTING: COMPATIBLE WITH GERMATECH BASE COAT SYSTEM – TINT 50/50 ON STANDARD COLOURS. CHECK OPACITY AND ON LOWER COVERAGE COLOURS TINT 60/40 BASE TO BINDER

MIXING:

MIX BY VOLUME

1 : 1 (0-30%)

MUST SPRAY USING

1.2-1.4 MM TIP

2-2.5 BAR HVLP

DRY TIME:

FLASH OFF 2-3 MIN BETWEEN COATS

ALLOW 15 - 20 MIN IF BAKING

AIRDRY 1 - 2 HOURS AT 20°

MICRONS:

2-3 COATS

40 UM (MICRON) MAX

Do not exceed micron max